



PRODUCT PROFILE

DESCRIPTION

GRAFFITI GARD® IV (GLOSS) is a non-sacrificial, two-component, water-based high performance clear aliphatic urethane coating that resists graffiti from a variety of materials including spray paints and marking pens. In many cases, freshly applied wet spray paint/ink will actually crawl back onto itself, frustrating the would-be tagger into stopping and moving on to another target. The slick surface is easy to clean with GRAFFITI GARD® IV BIODEGRADABLE CLEANER followed by power washing.

FEATURES

- Simple To Mix and Apply
- Water-Based Formula
- Excellent Graffiti Resistance
- Excellent UV Resistance
- Easy Removal of Graffiti
- Breathable Coating
- Low VOC

BENEFITS

- Protects Surface Against Graffiti
- Water Repellant Surface Stays Clean Looking
- Easy Removal of Graffiti
- Low VOC; Able To Be Used in All States/Jurisdictions

RECOMMENDED PRIMERS/SUBSTRATES

Can be used over many interior and exterior vertical surfaces including Bare Concrete, Split Face Block, clean and sound previously coated Concrete, Brick, properly prepared previously coated Metal, and other manufacturer-approved surfaces.

PRODUCT APPLICATION

APPLICATION EQUIPMENT

Application of GRAFFITI GARD® IV can be done by brush, roller, or airless sprayer. When spraying product, proper respiratory protection is required. Airless sprayer should use .011-.013 spray tip.

GENERAL / SURFACE PREPERATION

Proper surface preparation is essential to achieve the proper results with GRAFFITI GARD® IV. All surfaces must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, and other foreign material to ensure proper adhesion. If the surface is previously painted, ensure that it is in sound condition and cleaned of all contaminants. Smooth or glossy coatings should be dulled by abrading the surface, and then all dust removed from the surface. In cases of directly applying to metal, cross-hatch adhesion tape test should be used to ensure adequate bonding. Adjacent surfaces not to be coated must be masked.

PRIMER SYSTEM

When applied to a porous masonry surface such as split-face block, the substrate should be primed with RAINSTOPPER® 1750W Clear. Previously painted substrates do not need priming.

APPLICATION RATE

The actual application rate is dependent on the texture and absorbance of the surface being treated. Typical application rates will be 250-350 square feet per gallon. Textured or absorbent surfaces will require additional material.

For extended warranty, a second coat must be applied as soon as possible after the first coat has set to touch, typically within 1-2 hours. Waiting longer may result in the additional material being repelled by the previous coat. Do not over apply film build as excessive thickness may create milky appearance through air entrapment.

MIXING

GRAFFITI GARD® IV is a two-component product that must be mixed together prior to doing the application. Open both containers and add the clear Part B slowly while mixing into the Part A container.

(Note: 5/gal kit requires mixing in two Part B containers). Mix approximately 2-3 minutes until smooth and uniform. Do not over mix or foam bubbles may be created. Once mixed, you will have 1-2 hours of working time to apply mixed product. The usable pot life is temperature dependent and is shorter at higher temperatures. Product should not be thinned or diluted.

APPLICATION

GRAFFITI GARD® IV should be applied in a timely manner, thus planning the application is important. A mock-up sample application is recommended for final approval by architect, engineer, or contractor of the surface appearance.

SAFETY

Apply with adequate ventilation. Follow all safety precautions including proper respiratory protection as noted in the Material Safety Data Sheet (MSDS).

CLEAN-UP

Clean equipment promptly with soap and water.



TECHNICAL DATA SHEET

Anti-Graffiti Coating Systems GRAFFITI GARD® IV (GLOSS)

PRODUCT APPLICATION

GRAFFITI REMOVAL

Graffiti should be removed as soon as possible. Spray paint graffiti should be removed with GRAFFITI GARD® IV BIODEGRADABLE CLEANER followed by power-washing. Cleaner should be applied by brush or roller, allow to remain on surface 10 minutes, then scrubbed with a bristle brush, wait an additional 5 minutes, and power wash. Additional application of CLEANER may be necessary for complete graffiti removal. Graffiti not removed in the first few weeks may result in ghosting after cleaning.

REPAINTING

Prior to repainting or top coating Graffiti GARD® IV, abrading the surface substrate will be necessary. Light sanding or using steel wool are acceptable ways to remove the anti-graffiti properties.

BEST PERFORMANCE

IMPORTANT STEPS

- Follow all instructions closely for surface preparation, mixing, and application.
- Adjacent surfaces not to be coated should be well masked.
- Apply under ideal weather conditions with temperatures between 50°F-90°F.
- Shelf life is 6 months at room temperature. Containers should be stored upright and sealed.
- Periodic cleaning with a power-washer will remove any atmospheric dust or dirt residues and keep the surface fresh looking.

TECHNICAL DATA

PHYSICAL PROPERTY	TYPICAL RESULT
Coverage Rate	250-350 sq ft/gallon
Density Part A	8.6, Typical
Density Part B	9.6, Typical
Density Mixed	8.9, Typical

PHYSICAL PROPERTY	TYPICAL RESULT
Gloss @ 60 Degrees	75 Minimum
Pot Life	1-2 Hours
VOC (grams/liters minus water)	< 50 grams/Liter)
Volume Percent Mixed A/B	48-52%

Applicable Standards | American Society for Testing Materials (ASTM)

TEST METHOD	PROPERTY	RESULT
ASTM D1653	Moisture Vapor Transmission	6 Perms
ASTM C666	Freeze/Thaw	Durability @ 300 Cycles - 98.3% Weight Loss @ 300 Cycles - 0% Surface Rating (Per C672) - No Scaling
ASTM D7089	Graffiti Cleanability	100% Graffiti removal of black solvent spray paint cured for 24 hours.
ASTM C666	Freeze/Thaw Modified with Saline	No visible changes nor signs of cracking or delamination @ 300 cycles.
ASTM G154	Accelerated Weathering	Observations @ 1500 Hours - No cracking, loss of adhesion or discoloration.
ASTM D4060	Abrasion Resistance	0.0145 Wear Index @ 1000 Cycles (Excellent)
ASTM D1308	Chemical Resistance to Household Chemicals	Exhibit excellent resistance to chemical agents when exposed.



TECHNICAL DATA SHEET

Anti-Graffiti Coating Systems GRAFFITI GARD® IV (GLOSS)

ORDER INFORMATION

PACKAGING

GRAFFITI GARD® IV is a clear two-component finish that is available in either 0.9 gallon or five (5) gallon kits.

The kit is comprised of a Part A and Part B component.

Note: Five (5) gallon kit is comprised of one Part A component and two Part B components.

SHELF-LIFE

6-Month Shelf Life under proper conditions:

- Containers are sealed, upright and airtight in a dry place.
- Maintain temperature of 45°F to 100°F (7°C to 37.7°C).
- AVOID FREEZING.

SAFETY

WARNING

- Use protective clothes, glasses, and gloves when mixing and applying.
- Use with adequate ventilation.
- When applying by spray, proper respiratory protective equipment must be worn.
- Follow recommendations on Safety Data Sheets (SDS).

VOC COMPLIANCE

All TEX-COTE® products comply with federal Volatile Organic Compound (VOC) rules and regulations.

Please contact your nearest TEX-COTE LLC office for assistance on the local and state VOC compliance in the area of intended use.

WARRANTY

Upon completion of the application of the coating in accordance with the manufacturer's recommendations, TEX-COTE LLC will extend its limited commercial warranty for product replacement as a result of a defect in the material. The manufacturer must be notified prior to the application of the coating and the application must be in compliance with the manufacturer's recommendations for installation. TEX-COTE LLC shall have no obligation to contribute to or otherwise participate in labor or cost associated with effecting repairs. Specimen copy of material warranty is available upon request.

Corporate HQ & East Coast Facility

2422 E. 15th St., Panama City, FL 32405 | 800-454-0340 | 850-769-0347 | Fax 850-913-8619

South Florida Sales Office

7000 W. Palmetto Park Rd., Ste 210-W14, Boca Raton, FL 33433 | 954-581-0771 | Fax 954-581-9516

West Coast Facility

417 E. Weber Ave., Compton, CA 90222 | 323-233-3111 | Fax 310-438-2873